



ASC Building Products Color Performance Data

Please note that color specific *CRRC Notification of Product Rating* can be produced upon request

PRODUCT DESCRIPTION	CA TITLE 24 & ENERGY STAR					LEED							
	via CRRC listings (data based on color families)				Energy Star	CA Title 24	via Accredited Independent Testing Laboratory (using ASTM C1549, C1371, & E1980)						
	CRRC Reference Number	Solar Reflectance (Init.)	Thermal Emittance (Init.)	SRI Init.	Low Slope	Steep Slope	Solar Reflectance (Init.)	Thermal Emittance (Init.)	SRI Init.	Low Slope (Leed V3)	Steep Slope (Leed V3)	Low Slope (Leed V4)	Steep Slope (Leed V4)
BARE ZINCALUME®													
ZINCALUME® Plus	1014-0002	0.68	0.30	65	✓	✓	0.68	0.30	65		✓		✓
DURATECH™ XL COLORS													
COOL TAHOE BLUE	0818-0027	0.25	0.83	22		✓	0.33	0.84	33		✓		
COOL OLD TOWN GRAY	0818-0039	0.35	0.83	35		✓	0.40	0.84	43		✓		✓
COOL DENALI GREEN	0818-0028	0.25	0.83	22		✓	0.30	0.83	29		✓		
COOL RUSTIC RED	0818-0031	0.35	0.83	35		✓	0.40	0.84	43		✓		✓
COOL LIGHT STONE	0818-0033	0.55	0.83	63		✓	0.60	0.84	70		✓		✓
COOL DESERT BEIGE	0818-0042	0.45	0.83	49		✓	0.51	0.84	58		✓		✓
COOL CHESTNUT BROWN	0818-0034	0.32	0.83	31		✓	0.35	0.83	36		✓		
COOL WEATHERED COPPER	0818-0035	0.32	0.83	31		✓	0.32	0.83	32		✓		
COOL WINTER WHITE	0818-0044	0.70	0.83	84	✓	✓	0.73	0.83	88	✓	✓	✓	✓
COOL SURF WHITE	0818-0036	0.55	0.83	63		✓	0.63	0.84	74		✓		✓
COOL CYPRESS GREEN	0818-0023	0.25	0.83	22		✓	0.30	0.84	29		✓		
COOL CANYON RED	0818-0024	0.35	0.83	35		✓	0.42	0.84	45		✓		✓
COOL TAUPE	0818-0025	0.45	0.83	49		✓	0.48	0.83	53		✓		✓
COOL FOREST GREEN	0818-0029	0.32	0.83	31		✓	0.35	0.85	36		✓		
COOL COPPER PENNY	0818-0032	0.35	0.75	32		✓	0.49	0.84	55		✓		✓
COOL CLASSIC BROWN	0818-0041	0.25	0.83	22		✓	0.29	0.84	29		✓		
COOL EVERGLADE	0818-0043	0.32	0.83	31		✓	0.34	0.85	35		✓		
COOL BLACKBERRY	0818-0050	0.25	0.83	22		✓	0.33	0.85	34		✓		
COOL OLD ZINC GRAY	0818-0051	0.35	0.83	35		✓	0.40	0.84	43		✓		✓
COOL TUMBLEWEED	0818-0052	0.55	0.83	63		✓	0.62	0.84	73		✓		✓

REFER TO CALIFORNIA ENERGY COMMISSION (CEC) REQ.

All ratings listed above are initial readings. Three year performance data is located on the CRRC website and is based on CRRC color families.

^A - Reflectivity data for Bare ZINCALUME is actual 3 year weathered solar reflectivity data.

ZINCALUME® is a registered trademark of BlueScope LTD

Rev.10-24-17